

Produktdatenblatt
Product datasheet

duraskin® B4951 OPAQUE

Faserstoff des Trägergewebes Support cloth Tissu	DIN 60001	PES diolen® SLC anti-wicking
Beschichtungsart Type of coating Nature de l'enduit		PVC PVC PVC
Schlusslack Top Coat Équipement de surface		verschw. PVDF-Lack weldable PVDF laquer Laque PVDF
Flächengewicht Total weight Masse totale	DIN EN ISO 2286-2	850 g/m ²
Breite Width Largeur	DIN EN ISO 2286-1	250 / 300 cm
Höchstzugkraft K/S Tensile strength warp/weft Resistance a la traction en chaine/en trame	DIN EN ISO 1421	3000 / 3000 N/5 cm
Weiterreißkraft K/S Tear Resistance Resistance à la Déchirure en chaine/en trame	DIN 53363	300 / 300 N
Haftung Adhesion Adhésion	DIN 53357	100 N/5 cm
Opazität Opacity Opacité	DIN 5036 (550 nm)	100 %
Anwendung Application Application		Membranen membranes membranes
Brandverhalten Flame Retardancy Réaction au feu	DIN 4102	B1

Bemerkung / Comment:

- Hochfrequenz-Verschweißung empfohlen
- high-frequency welding recommended

